

Technical Data Sheet PP PPG 2019-25 LUKOIL

DOW Chemical License.

Application area:

Polypropylene PPG 2019-25 intended for the manufacture of blown products, transparent containers for hot filling, extrusion multilayer sheets.

Melt flow index, g / 10 min (at 2.16 kg / 230 ° C)	1,9-2,2
Variation of the melt flow index values within the batch, %	+ -10
Tensile stress at yield, MPa	26
Elongation at yield,%	9
Mass fraction of volatile substances %, not more than	0,09

Terms of Use:

Prior to processing bags with polymer shall be conditioned at least 12 hours in the production room.

Rules of storage:

Polypropylene and propylene copolymers are stored indoors, excluding direct sunlight, at a distance of at least 1 meter from heaters.

Polypropylene Storage temperature should be no higher than 30 ° C, relative humidity and less than 80%.

Guaranteed shelf life

Guaranteed shelf life of polypropylene and propylene copolymers - 3 years from date of manufacture when stored.