

Technical Data Sheet PP PPG 3008-36 LUKOIL

DOW Chemical License.

Application area:

Polypropylene PPG3008-36 intended for the manufacture of blown articles, sheets, plates, pipes.

Melt flow index, g / 10 min (at 2.16 kg / 230 ° C)	0,7-0,9
Variation of the melt flow index values within the batch, %	+ -10
Tensile stress at yield, MPa	21
Elongation at yield,%	9
Density, kg / m ³	880-920
Mass fraction of volatile substances %, not more than	0,09
The number of inclusions, not more than (pcs)	10
Izod impact strength with notch at 23 ° C not less than, J/m	441

Terms of Use:

Prior to processing bags with polymer shall be conditioned at least 12 hours in the production room.

Rules of storage:

Polypropylene and propylene copolymers are stored indoors, excluding direct sunlight, at a distance of at least 1 meter from heaters.

Polypropylene Storage temperature should be no higher than 30 ° C, relative humidity and less than 80%.

Guaranteed shelf life

Guaranteed shelf life of polypropylene and propylene copolymers - 3 years from date of manufacture when stored.